MATERIAL SAFETY DATA SHEET

REV: 05/18/05

U.S. OSHA HAZARD COMMUNICATION STANDARD, 29 CFR 1910.1200/ILL TSDA Pa 38-20

DULUTH BRASS	SECTION 1	COLOR TO THE STATE OF THE STATE
		EMERGENCY TELEPHONE NO.
MANUFACTURING		(312) 226-6600
2301 COMMONWEALTH AVENUE / DULUTH, MN 55808-1643		
218-626-2564 / FAX 218-626-2615		
CHEMICAL NAME and SYNONYMS		TRADE NAME and SYNONYMS
Manganese Bronze (58-39-1-1-1)		421 - 65,000 Tensile Mang. Bronze
CHEMICAL FAMILY	FORMULA	
N/A		ASTM C86500

SECTION II - HAZARDOUS INGREDIENTS					
			<u>PEL</u>	TLV	
ELEMENT	CAS NUMBER	PERCENTAGE	OSHA 8-HR TWA MG/M3	ACGIH 8-HR TWA MG/M3	
Copper	7440-50-8	55.00 - 60.00	0.1 (Fume)	0.1 (Fume)	
Tin	7440-31-5	1.00 Max	2	2	
Lead	7439-92-1	.30 Max	0.05 (Fume)	0.05 (Fume)	
Zinc	7440-66-6	36.00 - 42.00	5 (Oxide Fume)	5 (Oxide Fume)	
Iron	1309-37-1	.40 - 2.00	10 (Oxide Fume)	5 (Fume)	
Nickel	7440-02-0	.80 Max	1	1	
Aluminum	7429-90-5	.50 - 1.50	5 (Dust)	5 (Dust)	
Manganese	7439-96-5	.10 - 1.50	5 (Fume)	1 (Fume)	
manganoo	, ,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,				

** This material is inert and non-toxic in the solid state **

	5	ECTION III - PHYSICAL DA		
BOILING POINT (F°)			SPECIFIC GRAVITY (H ₂ O=1)	8.30
Copper	4703			
Tin	4120	N	lolten state operating temperature is 1800 to	2200 F
Lead	3137		<i>™</i>	
Zinc	1663			
Iron	5430			
Nickel	4900			
Aluminum	4442			
Manganese	3806			
:				
		APPEARANCE & ODOR:	Odorless yellow metal	

SECTION IV - FIRE and EXPLOSION HAZARD DATA

FLASH POINT (Method used)

N/A

EXTINGUISHING MEDIA

Dry chemicals or sand should be used with molten metals.

SPECIAL FIRE FIGHTING PROCEDURES

Fire Fighters should wear full protective clothing.

UNUSUAL FIRE AND EXPLOSION HAZARDS

DO NOT USE WATER ON MOLTEN METALS.

PAGE (1)

(CONTINUED ON REVERSE SIDE)

SI	CTION V - HEALTH HAZARD DATA		
THRESHOLD LIMIT VALUE			
	SEE SECTI	ON II	
EFFECTS OF OVEREXPOSURE			
	SEE ATTACHMENT ITEMS	8, 17, 10, 18, 9, 13, 1, 12	
	OLL III I I I I I I I I I I I I I I I I		
EMERGENCY AND FIRST AID PROCEDURES			Ař
	SEE ATTACHMENT ITEMS	8, 17, 10, 18, 9, 13, 1, 12	
	SEE ATTAOTAMENT THEMS		

SECTION VI - REACT	HVIIY DATA		1
UNSTABLE		CONDITIONS TO AVOID	
STABLE	X		N/A
VOID)			
	STRONG	OXIDIZERS	
UCTS			
		N/A	
MAY OCCUR			CONDITIONS TO AVOID
		X	N/A
	UNSTABLE STABLE VOID)	STABLE X VOID) STRONG UCTS MAY OCCUR	UNSTABLE CONDITIONS X STABLE X VOID) STRONG OXIDIZERS UCTS N/A MAY OCCUR

SECTION VII - SPILL OR LEAK PROCEDURES STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED Special care should be taken when handling molten metal. Always wear proper safety equipment. Accumulations of dust should be vacuumed or wet-swept to prevent airborne exposure. WASTE DISPOSAL METHOD Metal turnings, chips, risers, grindings, etc. are recycled. If not recycled, dispose of material in accordance with the requirements of 40 CFR subtitle C and other applicable federal, state, and local regulations.

	SECTION VIII - SPECIAL P	ROTECTION INFORMAT	ION
RESPIRATORY PROTECTION (SPECIFY TYPE)	NIOSH Certified (3M 9920, etc.)		
VENTILATION	LOCAL EXHAUST	X	SPECIAL
VENTION TO THE PROPERTY OF THE	MECHANICAL (GENERAL)		OTHER
PROTECTIVE GLOVES		EYE PROTECTION	
Industrial Type			Safety Glasses/Goggles/Shields
OTHER PROTECETIVE EQUIPMENT			

SECTION IX - SPECIAL PRECAUTIONS PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING Material in storage can become wet from condensation. It must be throughly dried before adding to molten metal. See other sections, references and sources.